

Sharpie Primer P50 Properties Data Sheet

Applicable Sealant	Other Than Silicone-Based And Water-Based	
Appearance	Yellowish Transparent Liquid	
Main Component	Urethane Type	
Main Solvent	Ethyl Acetate MCH Dimethyl Carbonate	35~45% 10~20% 15~25%
Solid Content	30~32%	
Weatherability / Yellowing	Do Not Yellowing	
Application Time	Within 8 Hours	
Tack Free Time	5°C	60 Mins~
	23°C	30 Mins~
	35°C	30 Mins~
Storage	12 Months	Unopened, Stored In A Cool Dark Place
Adhesion Property	Aluminum: ◎	Under Jis A 5758 Durability Test
	Mortar: ◎	
<p>▼Notes▼</p> <ul style="list-style-type: none"> - Apply primer before using sealant. - Clean the joints and ensure the surface is dry before applying primer. - Do not reuse the brush during application. - Take care to avoid protruding or scattering during installation. - After opening, divide the needed amount into smaller portions and promptly seal the container when not in use. - If the viscosity increases or moisture is mixed in, do not use. - If it has been over 8 hours since applying the primer, please reapply. - Using primer is highly recommended for long-term adhesion of the sealant. - Consider the surface treatment or painting process of the adherend, as it may affect adhesion. - Adhesiveness may vary based on construction conditions and the surface condition of the adherend. 		